

Titanium Lustre 280gsm

Digital & Fine Art Archival Printing Solutions for the Imagemaker

Description of Product:

Titanium Lustre has a beautiful pronounced textured finish on a heavyweight 280gsm base. Incredible detail and clarity is achievable delivering stunning high resolution visual impact and making your images just jump off the paper with the dramatic metallic appearance.

A material that has a great tonal range, wide colour gamut and a high D-max rating which will work extremely well with images that have vibrant colours, deep blacks and shiny white/silver areas. Ideal for images containing reflective metal surfaces such as chrome, silver or even gold and everyday objects such as watches, jewellery, glass, mirrors – the list is endless!

The instant you see and feel this material you will know that it is a true quality metallic paper with a real difference.

Technical Information:

- Weight – 280gsm
- Thickness – 0.28mm
- Whiteness – (CIE) 96
- Coatings – Single-sided, metallic resin coated lustre base
- Primary Features – High D-Max, Excellent tonal range, High colour gamut
- Optical Brightening Agents (OBA) - Yes

Media Availability:

Sheets	6"x4"	7"x5"	A4	A3	A3+	A2
Rolls	12"x25m	24"x30m	44"x30m	60"x30m		

Applications of Use:

Monochrome, Fine art reproductions, Wedding & portraiture, Photographic & portfolio applications.

Printer & Ink Compatibility:

PermaJet Titanium Lustre has been designed for use with Dye & Pigment inkjet systems. The media has been designed, manufactured and tested for use with Epson, HP, Canon and Lexmark printers.

Storage & Conditions of Use:

The storage and use of the product should be in a climate and a temperature of 15 to 30° C at a relative humidity of 30 to 60%. Always keep the product in its original packaging or in archival quality folders. Where possible, always handle the paper or printed surface by its edges.

All recommendations and product indications are for guidance, and are subject to our test criteria, these remain subject to change without prior notice. There is no guarantee that the same results can be consistent.